ZI Haneboesch L-4562 Differdange LUXEMBOURG

Phone: +352 58 22 82 1 Fax: +352 58 49 35

E-mail: sales@airtech.lu Website: www.airtech.lu

# Data Sheet

# **WRIGHTLON® 600V**

# Low cost nylon vacuum bagging film

### **DESCRIPTION**

Wrightlon® 600V vacuum bagging film is designed for low cost, commercial applications yet still performs with high pressure autoclave cure cycles. It has good elongation and stays soft in low humidity conditions.

#### **BENEFITS**

- Inexpensive film with good performance reduces the cost of commercial autoclave molding process.
- Good elongation and softness of film makes bagging easier and reduces cycle times.
- Combination of strength and elasticity improves part quality, reduces rework, and scrap.

#### **TECHNICAL DATA**

		Test method
Material type	Nylon	
Elongation at break	400 %	ASTM D 882
Tensile strength	65 MPa	ASTM D 882
Maximum use temperature	204°C	
Flammability (self extinguishing)	Yes	ATP-5034
Materials to avoid	Phenolic resins/Strong oxidizers	

Violet Colour

Shelf life Unlimited when stored in original packaging at 22°C

### **SIZES**

Thickness	Width	Forms Available*
50 μm (0,002 inch)	up to 7,11 m (280 inches)	SHT, CF, LFT
75 μm (0,003 inch)	up to 6,60 m (260 inches)	SHT, CF, LFT

- For more sizes, see the Commonly Used Sizes chart in this section.
- Custom shapes and sizes are available, please contact Airtech for more information.



\*SHT=Sheeting



CF=Centerfold



LFT=Lay-Flat Tubina



Tubing



## **NOTES**

• The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.

> Last updated: 2017-11-06 Catalogue position: Bagging films