

# Release Film

VABATEC® RF 2 is a cost-optimized PO release film with a very high elongation, which is suitable for use with all common resin systems up to 150 - 160 °C.

The film can be also supplied in a perforated version as VABATEC® RF 2 P3 and P5.

## PHYSICAL PROPERTIES

	Unit	Average	Method
Tensile strength (md)	MPa	> 50	EN ISO 527-3
Tensile strength (cd)	MPa	> 30	EN ISO 527-3
Elongation at break (md)	%	> 500	EN ISO 527-3
Elongation at break (cd)	%	> 700	EN ISO 527-3
Max. temperature 150 °C - 160 °C			

## PACK SIZES

Order Code	Desc.	Length	Width (mm)	Thickness	Perf.	Format
0-V12 760S	Release Film	100 Lm	1530	30 Micron	P3	Sheet
0-V12 740S	Release Film	100 Lm	1530	30 Micron	P3	Sheet

## STORAGE

VABATEC® RF 2 should be stored in original packaging, and kept dry and clean.

NOTE: Our products are intended for sale to industrial and commercial customers. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty or merchantability or fitness, nor is protection from law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials and in no event shall we be liable for special or consequential damages. 01.05.2024